

**AMENDMENTS TO THE CLAIMS**

1. (Cancelled).
2. (Currently Amended) The pneumatic tire ~~according to claim 1~~, wherein said at least one cord-reinforced layer is a carcass extending between bead portions through a tread portion and sidewall portions,  
said carcass comprising at least one ply of carcass cords extending between the bead portions,  
each said carcass cord being made up of seven to twelve metallic filaments whose diameter is in a range of from 0.15 to 0.30 mm,  
said seven to twelve metallic filaments being grouped into a plurality of elements, said plurality of elements being (i) bunches of two or three or four filaments, or (ii) one filament and bunches of two or three or four filaments,  
said plurality of elements being twisted at a twist pitch  $P_c$  of from 10 to 25 mm,  
each bunch including at least one waved filament and at least one unwaved filament,  
the waved filament being two-dimensionally waved at a wave pitch and wave height before being twisted, wherein the wave pitch is in a range of from 5.0 to 30.0 times the diameter of the filament, and the wave height is in a range of from 0.5 to 4.0 times the diameter of the filament.
3. (Original) The pneumatic tire according to claim 2, wherein the filaments in each said bunch are twisted at a twist pitch  $P_f$  of from 3 to 20 times the twist pitch  $P_c$ .
4. (Original) The pneumatic tire according to claim 2, wherein each said bunch is made up of two or three filaments.
5. (Original) The pneumatic tire according to claim 2, wherein  
the bunch includes plural kinds of waved filaments having different wave pitches.
6. (Cancelled).

7. (Cancelled).

8. (Cancelled).

9. (Cancelled).

10. (Cancelled).

11. (Cancelled).

12. (Currently Amended) The pneumatic tire according to claim 2 ~~1~~, wherein  
said at least one cord-reinforced layer is a bead reinforcing layer disposed in a bead  
portion,  
said bead reinforcing layer being made of bead reinforcing cords,  
each said bead reinforcing cord being made up of seven to twelve metallic filaments  
whose diameter is in a range of from 0.17 to 0.25 mm and a wrapping wire wound around the  
filaments and having a diameter in a range of from 0.13 to 0.17 mm,  
said metallic filaments including at least two waved filaments and at least three unwaved  
filaments,  
the waved filament two-dimensionally waved before twisted so as to be made up of  
straight segments in a zigzag formation,  
all the waved filaments having the same wave pitch and the same wave height, the wave  
pitch being in a range of from 10.0 to 35.0 times the diameter of the filament, and the wave height  
being in a range of from 0.5 to 4.0 times the diameter of the filament, and the value  $dXh/Pw$  is in a  
range of from 0.014 to 0.028,  
said seven to twelve metallic filaments being twisted at a twist pitch of from 10 to 30 mm  
while interchanging at least two of said seven to twelve metallic filaments in their relative  
positions,  
the wrapping wire being wound around the twisted filaments in a direction reverse to said  
twist direction at a winding pitch of 3.0 to 7.0 mm.

13. (Original) The pneumatic tire according to claim 12, wherein  
said seven to twelve metallic filaments are twisted such that  
all the filaments as a bunch are rotated around the axis of the bunch in a direction so that  
each filament is essentially subjected to a rotation around the axis of the filament in the  
same direction as said direction.

14. (Currently Amended) The pneumatic tire according to claim 1 2, wherein  
said at least one cord-reinforced layer is  
a carcass extending between bead portions through a tread portion and sidewall  
portions, and  
a belt disposed radially outside the carcass in the tread portion,  
said carcass comprising at least one ply of carcass cords extending between the bead portions,  
each said carcass cord being made up of seven to twelve metallic filaments whose diameter is in a range  
of from 0.15 to 0.30 mm, said seven to twelve metallic filaments being grouped into a plurality of  
elements, said plurality of elements being (i) bunches of two or three or four filaments, or (ii) one  
filament and bunches of two or three or four filaments, said plurality of elements being twisted at a twist  
pitch  $P_c$  of from 10 to 25 mm, each bunch including at least one waved filament and at least one  
unwaved filament, the waved filament being two-dimensionally waved at a wave pitch and wave height  
before being twisted, wherein the wave pitch is in a range of from 5.0 to 30.0 times the diameter of the  
filament, and the wave height is in a range of from 0.5 to 4.0 times the diameter of the filament, and  
said belt made of belt cords, each said belt: cord made up of six to ten metallic filaments  
whose diameter is in a range of from 0.25 to 0.45 mm, said six to ten metallic filaments being  
grouped into a plurality of elements, said plurality of elements being (i) bunches of two or three or  
four filaments, or (ii) one filament and bunches of two or three or four filaments, said plurality of  
elements being are twisted at a twist pitch  $P_c$  of from 10 to 40 mm, each bunch including at least one  
waved filament and at least one unwaved filament, the waved filament being two dimensionally  
waved at a wave pitch and wave height before twisted, wherein the wave pitch is in a range of from  
5.0 to 30.0 times the diameter of the filament, and the wave height is in a range of from 0.2 to 3.0  
times the diameter of the filament.

15. (Currently Amended) The pneumatic tire according to claim 2, ~~6 or 14~~, wherein said at least one cord-reinforced layer further includes a bead reinforcing layer disposed in a bead portion,

said bead reinforcing layer being made of bead reinforcing cords,

each said bead reinforcing cord being made up of seven to twelve metallic filaments whose diameter is in a range of from 0.17 to 0.25 mm and a wrapping wire wound around the filaments and having a diameter in a range of from 0.13 to 0.17 mm,

said metallic filaments including at least two waved filaments and at least three unwaved filaments,

the waved filament two-dimensionally waved before twisted so as to be made up of straight segments in a zigzag formation,

all the waved filaments having the same wave pitch and the same wave height, the wave pitch being in a range of from 10.0 to 35.0 times the diameter of the filament, and the wave height being in a range of from 0.5 to 4.0 times the diameter of the filament, and the value  $dX_h/P_w$  is in a range of from 0.014 to 0.028,

said seven to twelve metallic filaments being twisted at a twist pitch of from 10 to 30 mm while ~~interchanging~~ interchanging at least two of said seven to twelve metallic filaments in their relative position,

the wrapping wire being wound around the twisted filaments in a direction reverse to said twist direction at a winding pitch of 3.0 to 7.0 mm.

--16. (New) The pneumatic tire according to claim 14, wherein

said at least one cord-reinforced layer further includes a bead reinforcing layer disposed in a bead portion,

said bead reinforcing layer being made of bead reinforcing cords, each said bead reinforcing cord being made up of seven to twelve metallic filaments whose diameter is in a range of from 0.17 to 0.25 mm and a wrapping wire wound around the filaments and having a diameter in a range of from 0.13 to 0.17 mm,

said metallic filaments including at least two waved filaments and at least three unwaved filaments,

the waved filament two-dimensionally waved before twisted so as to be made up of straight segments in a zigzag formation,

all the waved filaments having the same wave pitch and the same wave height, the wave pitch being in a range of from 10.0 to 35.0 times the diameter of the filament, and the wave height being in a range of from 0.5 to 4.0 times the diameter of the filament, and the value  $dXh/Pw$  is in a range of from 0.014 to 0.028,

said seven to twelve metallic filaments being twisted at a twist pitch of from 10 to 30 mm while interchanging at least two of said seven to twelve metallic filaments in their relative positions,

the wrapping wire being wound around the twisted filaments in a direction reverse to said twist direction at a winding pitch of 3.0 to 7.0 mm.--